

Pilkington **Activ™** Range
Performance Data



Table 1 – Performance Data Pilkington **Insulight Activ™** with 6 mm Pilkington **Optifloat™** Clear inner pane unless otherwise indicated.

Product Description	Light		Solar Radiant Heat				Shading Coefficients			U _g -value (W/m ² K)	Unit Maximum Sizes		Descriptive Code
	Transmittance	Reflectance	Direct Transmittance	Reflectance	Absorptance	Total Transmittance (g value)	Short Wavelength	Long Wavelength	Total	Argon (90%)	Annealed (mm)	Toughened (mm)	
Pilkington Insulight Activ™ (with 4 mm Pilkington Optifloat™ Clear inner pane and 16 mm 90% argon filled cavity)													
4 mm Pilkington Activ™ Clear	0.77	0.20	0.70	0.19	0.11	0.74	0.80	0.05	0.85	2.6	2000×1200	2000×1500	77/74
4 mm Pilkington Activ™ Blue	0.53	0.18	0.39	0.15	0.46	0.45	0.45	0.07	0.52	2.6	2000×1200	2000×1500	53/45
4 mm Pilkington Activ™ Bronze	0.53	0.18	0.48	0.16	0.36	0.53	0.55	0.06	0.61	2.6	2000×1200	2000×1500	53/53
4 mm Pilkington Activ SunShade™ Neutral	0.45	0.30	0.41	0.24	0.35	0.47	0.47	0.07	0.54	2.6	2000×1200	2000×1500	45/47
4 mm Pilkington Activ SunShade™ Blue	0.29	0.22	0.21	0.17	0.62	0.28	0.24	0.08	0.32	2.5	2000×1200	2000×1500	29/28
Pilkington Insulight Activ™ (with 4 mm Pilkington K Glass™ inner pane and 16 mm 90% argon filled cavity)													
4 mm Pilkington Activ™ Clear	0.71	0.23	0.59	0.21	0.19	0.70	0.68	0.12	0.80	1.5	2000×1200	2000×1500	71/70
4 mm Pilkington Activ™ Blue	0.49	0.19	0.33	0.16	0.51	0.41	0.38	0.09	0.47	1.5	2000×1200	2000×1500	49/41
4 mm Pilkington Activ™ Bronze	0.49	0.19	0.40	0.18	0.42	0.49	0.46	0.10	0.56	1.5	2000×1200	2000×1500	49/49
4 mm Pilkington Activ SunShade™ Neutral	0.42	0.31	0.35	0.25	0.40	0.43	0.40	0.09	0.49	1.5	2000×1200	2000×1500	42/43
4 mm Pilkington Activ SunShade™ Blue	0.27	0.22	0.18	0.17	0.65	0.25	0.21	0.08	0.29	1.5	2000×1200	2000×1500	27/25
Pilkington Insulight Activ™ (with 4 mm Pilkington K Glass™ S inner pane and 16 mm 90% argon filled cavity)													
4 mm Pilkington Activ™ Clear	0.75	0.17	0.57	0.25	0.17	0.67	0.66	0.11	0.77	1.2	2000×1200	2000×1500	75/67
4 mm Pilkington Activ™ Blue	0.52	0.17	0.33	0.16	0.51	0.39	0.38	0.07	0.45	1.2	2000×1200	2000×1500	52/39
4 mm Pilkington Activ™ Bronze	0.51	0.17	0.39	0.20	0.41	0.47	0.45	0.09	0.54	1.2	2000×1200	2000×1500	51/47
4 mm Pilkington Activ SunShade™ Neutral	0.44	0.29	0.34	0.26	0.40	0.41	0.39	0.08	0.47	1.2	2000×1200	2000×1500	44/41
4 mm Pilkington Activ SunShade™ Blue	0.28	0.22	0.18	0.17	0.65	0.24	0.21	0.07	0.28	1.2	2000×1200	2000×1500	28/24
Pilkington Insulight Activ™ (with 4 mm Pilkington Optitherm™ S3 inner pane and 16 mm 90% argon filled cavity)													
4 mm Pilkington Activ™ Clear	0.75	0.18	0.52	0.33	0.15	0.59	0.60	0.08	0.68	1.1	2000×1200	2000×1500	75/59
4 mm Pilkington Activ™ Blue	0.52	0.17	0.31	0.18	0.51	0.36	0.36	0.05	0.41	1.1	2000×1200	2000×1500	52/36
4 mm Pilkington Activ™ Bronze	0.52	0.17	0.35	0.23	0.42	0.41	0.40	0.07	0.47	1.1	2000×1200	2000×1500	52/41
4 mm Pilkington Activ SunShade™ Neutral	0.44	0.29	0.31	0.29	0.40	0.36	0.36	0.05	0.41	1.1	2000×1200	2000×1500	44/36
4 mm Pilkington Activ SunShade™ Blue	0.29	0.22	0.17	0.18	0.65	0.22	0.20	0.05	0.25	1.1	2000×1200	2000×1500	29/22
Pilkington Insulight Activ™ (with 4 mm Pilkington Optitherm™ S1 Plus inner pane and 16 mm 90% argon filled cavity)													
4 mm Pilkington Activ™ Clear	0.72	0.22	0.46	0.39	0.15	0.52	0.53	0.07	0.60	1.0	2000×1200	2000×1500	72/52
4 mm Pilkington Activ™ Blue	0.50	0.19	0.28	0.19	0.53	0.33	0.32	0.06	0.38	1.0	2000×1200	2000×1500	50/33
4 mm Pilkington Activ™ Bronze	0.49	0.19	0.31	0.26	0.43	0.36	0.36	0.05	0.41	1.0	2000×1200	2000×1500	49/36
4 mm Pilkington Activ SunShade™ Neutral	0.42	0.31	0.28	0.31	0.41	0.32	0.32	0.05	0.37	1.0	2000×1200	2000×1500	42/32
4 mm Pilkington Activ SunShade™ Blue	0.27	0.22	0.16	0.18	0.66	0.20	0.18	0.05	0.23	1.0	2000×1200	2000×1500	27/20
Pilkington Insulight Activ™ (with 6 mm Pilkington Optifloat™ Clear inner pane and 16 mm 90% argon filled cavity)													
6 mm Pilkington Activ™ Clear	0.75	0.20	0.63	0.18	0.19	0.71	0.72	0.10	0.82	2.6	2500×1500	4000×2000	75/71
6 mm Pilkington Activ SunShade™ Neutral	0.44	0.29	0.36	0.22	0.42	0.44	0.41	0.10	0.51	2.5	2500×1500	4000×2000	44/44
6 mm Pilkington Activ™ Blue	0.44	0.16	0.28	0.14	0.58	0.36	0.32	0.09	0.41	2.6	2500×1500	4000×2000	44/36
Pilkington Insulight Activ™ (with 6 mm Pilkington K Glass™ inner pane and 16 mm 90% argon filled cavity)													
6 mm Pilkington Activ™ Clear	0.69	0.22	0.55	0.21	0.24	0.68	0.63	0.15	0.78	1.5	2500×1500	4000×2000	69/68
6 mm Pilkington Activ SunShade™ Neutral	0.40	0.30	0.31	0.23	0.46	0.41	0.36	0.11	0.47	1.5	2500×1500	4000×2000	40/41
6 mm Pilkington Activ™ Blue	0.40	0.17	0.24	0.14	0.62	0.32	0.28	0.09	0.37	1.5	2500×1500	4000×2000	40/32
Pilkington Insulight Activ™ (with 6 mm Pilkington K Glass™ S inner pane and 16 mm 90% argon filled cavity)													
6 mm Pilkington Activ™ Clear	0.72	0.17	0.52	0.34	0.24	0.65	0.60	0.15	0.75	1.2	2500×1500	4000×2000	72/65
6 mm Pilkington Activ SunShade™ Neutral	0.42	0.28	0.30	0.24	0.46	0.39	0.34	0.11	0.45	1.2	2500×1500	4000×2000	42/39
6 mm Pilkington Activ™ Blue	0.42	0.15	0.24	0.14	0.62	0.31	0.28	0.08	0.36	1.2	2500×1500	4000×2000	42/31
Pilkington Insulight Activ™ (with 6 mm Pilkington Optitherm™ S3 inner pane and 16 mm 90% argon filled cavity)													
6 mm Pilkington Activ™ Clear	0.73	0.18	0.48	0.31	0.21	0.57	0.55	0.11	0.66	1.1	2500×1500	4000×2000	73/57
6 mm Pilkington Activ SunShade™ Neutral	0.43	0.28	0.28	0.27	0.44	0.35	0.32	0.08	0.40	1.1	2500×1500	4000×2000	43/35
6 mm Pilkington Activ™ Blue	0.43	0.15	0.23	0.15	0.62	0.29	0.26	0.07	0.33	1.1	2500×1500	4000×2000	43/29
Pilkington Insulight Activ™ (with 6 mm Pilkington Optitherm™ S1 Plus inner pane and 16 mm 90% argon filled cavity)													
6 mm Pilkington Activ™ Clear	0.70	0.22	0.44	0.37	0.19	0.51	0.51	0.08	0.59	1.0	2500×1500	4000×2000	70/51
6 mm Pilkington Activ SunShade™ Neutral	0.41	0.29	0.26	0.29	0.45	0.31	0.30	0.06	0.36	1.0	2500×1500	4000×2000	41/31
6 mm Pilkington Activ™ Blue	0.41	0.17	0.21	0.16	0.63	0.26	0.24	0.06	0.30	1.0	2500×1500	4000×2000	41/26

All performance data determined in accordance with EN 410 and EN 673.

Table 2 – Performance Data Pilkington **Insulight Activ™** with 6 mm Pilkington **Optifloat™** Clear inner pane.

Product Description	Light		Solar Radiant Heat				Shading Coefficients			U _g -value (W/m ² K)	Unit Maximum Sizes		Descriptive Code
	Transmittance	Reflectance	Direct Transmittance	Reflectance	Absorptance	Total Transmittance (g value)	Short Wavelength	Long Wavelength	Total	Argon (90%)	Annealed (mm)	Toughened (mm)	
Pilkington Insulight Activ™ (with 6 mm Pilkington Optifloat™ Clear inner pane and 16 mm 90% argon filled cavity)													
6 mm Pilkington Activ Suncool™ 70/40	0.65	0.16	0.36	0.38	0.26	0.40	0.41	0.05	0.46	1.1	2500×1500	4000×2000	65/40
6 mm Pilkington Activ Suncool™ 70/35	0.65	0.21	0.32	0.44	0.24	0.35	0.37	0.03	0.40	1.0	2500×1500	4000×2000	65/35
6 mm Pilkington Activ Suncool™ 66/33	0.61	0.21	0.31	0.44	0.25	0.34	0.36	0.03	0.39	1.0	2500×1500	4000×2000	61/34
6 mm Pilkington Activ Suncool™ Silver 50/30	0.47	0.42	0.27	0.52	0.21	0.30	0.31	0.03	0.34	1.0	2500×1500	4000×2000	47/30
6 mm Pilkington Activ Suncool™ Blue 50/27	0.47	0.24	0.23	0.39	0.38	0.27	0.27	0.04	0.31	1.1	2500×1500	4000×2000	47/27
6 mm Pilkington Activ Suncool™ 50/25	0.47	0.23	0.23	0.42	0.35	0.26	0.26	0.04	0.30	1.0	2500×1500	4000×2000	47/26
6 mm Pilkington Activ Suncool™ 40/22	0.37	0.25	0.19	0.44	0.37	0.21	0.22	0.02	0.24	1.1	2500×1500	4000×2000	37/21
6 mm Pilkington Activ Suncool™ 30/17	0.28	0.30	0.15	0.46	0.39	0.17	0.17	0.03	0.20	1.1	2500×1500	4000×2000	28/17

All performance data determined in accordance with EN 410 and EN 673.

This publication provides only a general description of the products. Further, more detailed, information may be obtained from your local supplier of Pilkington products. It is the responsibility of the user to ensure that the use of these products is appropriate for any particular application and that such use complies with all relevant legislation, standards, codes of practice and other requirements. To the fullest extent permitted by applicable laws, Nippon Sheet Glass Co. Ltd. and its subsidiary companies disclaim all liability for any error in or omission from this publication and for all consequences of relying on it. Pilkington and "Insulight", "Optifloat", "Activ", "SunShade", "K Glass", "Optitherm", "Suncool" are trademarks owned by Nippon Sheet Glass Co. Ltd, or a subsidiary thereof.



CE marking confirms that a product complies with its relevant harmonised European Norm.
The CE marking label for each product, including declared values, can be found at www.pilkington.com/CE



Pilkington United Kingdom Ltd
European Technical Centre
Hall Lane, Lathom, Nr. Ormskirk, Lancs L40 5UF United Kingdom
pilkington@respond.uk.com
www.pilkington.co.uk