



Pilkington **Optiwhite™** performance data

Product	Light (%)		Solar Radiant Heat (%)				U _g -value [W/m ² K]
	Transmittance	Reflectance	Direct Transmittance	Reflectance	Absorptance	Total Transmittance	
2 mm	92	8	91	8	1	91	5.8
3 mm	92	8	91	8	1	91	5.8
4 mm	92	8	91	8	1	91	5.8
5 mm	91	8	90	8	2	90	5.7
6 mm	91	8	90	8	2	90	5.7
8 mm	91	8	89	8	3	90	5.6
10 mm	91	8	88	8	4	89	5.6
12 mm	91	8	88	8	4	89	5.5
15 mm	90	8	87	8	5	88	5.4
19 mm	90	8	86	8	7	87	5.3

The above performance data has been determined in accordance with EN 410 and EN 673.

This publication provides only a general description of the products. Further, more detailed, information may be obtained from your local supplier of Pilkington products. It is the responsibility of the user to ensure that the use of these products is appropriate for any particular application and that such use complies with all relevant legislation, standards, codes of practice and other requirements. To the fullest extent permitted by applicable laws, Nippon Sheet Glass Co. Ltd. and its subsidiary companies disclaim all liability for any error in or omission from this publication and for all consequences of relying on it. Pilkington and "Optiwhite" are trademarks owned by Nippon Sheet Glass Co. Ltd, or a subsidiary thereof.



CE marking confirms that a product complies with its relevant harmonised European Norm.

The Declaration of Performance for each product, including declared values, can be found at www.pilkington.com/CE



Pilkington Group Limited

European Technical Centre

Hall Lane – Lathom Nr Ormskirk L40 5UF – United Kingdom

marketing.communications@nsg.com

www.pilkington.com

March 2024